

Alloy Steels – AISI Designations

Alloy steels differ from carbon steels in that they have compositions that extend beyond the limits set for carbon steels. Usually this refers to constituents such as boron, carbon, chromium, manganese, molybdenum, silicon and vanadium. They also have chromium contents less than 4%. Steels with chromium contents of greater than 4% become classified as stainless or tool steels. As a general guide, an alloy steel will have:

Manganese content >1.65%

Silicon content >0.5%

Copper content >0.6%

The American Iron and Steel Institute (AISI) naming system is one of the most widely accepted systems.

Designations usually consist of a four digit number, but sometimes this extends to five. The first two digits indicate what the major alloying element is, while the last 2 or three indicate the carbon content in hundredths of a percent.

Example: AISI 1340 is a manganese containing alloy steel with a 0.40% average carbon content.

The below table summarizes AISI designations for alloy steels

Steel Type	AISI Grade	Ni	Cr	C	Mo	Mn	W	V	Si
CARBON STEELS	11xx	Resulfurized free machining							
	12xx	Resulfurized / Rephosphorized free machining							
MANGANESE STEEL	10xx					<1.00			
	15xx					1.00-1.65			
NICKEL STEELS	13xx					1.75			
	23xx	3.50							
NICKEL-CHROMIUM STEELS	25xx	5.00							
	31xx	1.25	0.65-0.80						
CHROMIUM-MOLYBDENUM STEELS	32xx	1.75	1.07						
	33xx	3.50	1.50-1.57						
MOLYBDENUM STEELS	34xx	3.00	0.77						
	40xx				0.20-0.25				
CHROMIUM-MOLYBDENUM STEELS	44xx				0.40-0.52				
	41xx		0.50-0.95		0.12-0.30				
NICKEL-CHROMIUM-MOLYBDENUM STEELS	43xx	1.82	0.50-0.80		0.25				
	47xx	1.05	0.45		0.20-0.35				
NICKEL-MOLYBDENUM STEELS	46xx	0.85-1.82			0.20-0.25				
	48xx	3.50			0.25				
CHROMIUM STEELS	50xx		0.27-0.65						
	51xx		0.80-1.05						
CHROMIUM-VANADIUM STEELS	50xxx		0.50	min 1.00					
	51xxx		1.02	min 1.00					
TUNGSTEN-CHROMIUM STEELS	52xxx		1.45	min 1.00					
	61xx		0.60-0.95					0.10-0.15	
NICKEL-CHROMIUM-MOLYBDENUM STEELS	72xx		0.75				1.75		
	81xx	0.30	0.40		0.12				
NICKEL-MANGANESE STEELS	86xx	0.55	0.50		0.20				
	87xx	0.55	0.50		0.25				
NICKEL-CHROMIUM-MOLYBDENUM STEELS	88xx	0.55	0.50		0.20-0.35				
	92xx		<0.65			0.65-0.85			1.40-2.00
NICKEL-CHROMIUM-MOLYBDENUM STEELS	93xx	3.25	1.20		0.12				
	94xx	0.45	0.40		0.12				
NICKEL-CHROMIUM-MOLYBDENUM STEELS	97xx	0.55	0.20		0.20				
	98xx	1.00	0.80		0.25				



THE SOURCE FOR ALL YOUR WELDING PRODUCTS