



Smoothcor[®] 81T1-Ni1

Classification: AWS A5.29 / ASME SFA 5.29 E81T1-Ni1C / E81T1-Ni1M

Description: Smoothcor 81T1-Ni1 is a low alloy steel flux cored wire intended for single and multiple pass welding, in all positions, on carbon and low alloy steels requiring good CVN toughness at subzero temperatures and greater than 80,000 psi tensile strength. Smoothcor 81T1-Ni1 applications include ASTM A572, A302, A588 and A734. It is used in the fabrication of transmission poles, light poles, earthmoving, and mining machinery and offshore platforms. It has spray-like arc transfer with low spatter, moderate slag volume that is removed easily.

Shielding Gas: 100% CO₂, 75% Ar/25% CO₂40-55 cfh

Typical Deposit Chemistry: %

	C	Mn	P	S	Si	Ni
CO ₂	.04	1.04	.01	.01	.44	1.0
75Ar/25CO ₂	.04	1.15	.01	.01	.47	.98

Typical Mechanical Properties:

	CO ₂	75Ar/25CO ₂
Tensile Strength(psi)	83,500	90,600
Yield Strength (psi)	76,900	76,100
Elongation	24	23
CVN (ft•lb f) @ 0°F	30	53

Typical Welding Parameters – Carbon & Low Alloy – Flux Cored -All position-CO₂*- DCEP

Dia.	Position	Operating Range		Optimum			
		Amps	Volts	Amps	WFS (ipm)	Volts	ESO
.045"	Flat	130-300	21-32	250	450	28	½ - 1"
	Overhead	150-280	21-30	190	305	26	½ - 1"
	Vertical Up	130-260	21-29	190	305	25	½ - 1"
.052"	Flat	140-330	19-32	275	400	28	½ - 1"
	Overhead	150-290	21-28	200	245	26	½ - 1"
	Vertical Up	140-270	21-27	200	245	25	½ - 1"
1/16"	Flat	150-400	22-34	330	330	29	½"-1"
	Overhead	150-310	22-28	225	180	26	½ -1"
	Vertical Up	150-280	22-27	225	180	25	½ - 1"

*For 75Ar/25CO₂ decrease voltage by 1 to 1.5 volts.

Notice: The results reported are based upon testing of the product under controlled laboratory conditions in accordance with American Welding Society Standards. Actual use of the product may produce different results due to varying conditions. An example of such conditions would be electrode size, plate chemistry, environment, weldment design, fabrication methods, welding procedure and service requirements. Thus, the results are not guarantees for use in the field. The manufacturer disclaims any warranty of merchantability or fitness for any purpose with respect to its products.